

Technical Data Sheet

Applications

- Extrusion coatings/laminations
- Heat seal layers
- Tie layers
- Compatibilizers
- Non-skid surfaces

Key Attributes

- Good adhesion to & compatibility with various polymers
- Low temperature heat & RF sealing
- Low Temperature flexibility
- Soft & flexible without plasticizers
- High coefficient of friction

Product Description

EMAC® SP2409 is a 20% EMA copolymer designed for extrusion coating, tie-layers, and extrusions where flexibility, compatibility, low heat seal temperatures, or high coefficient of friction are required. EMAC® SP2409 provides excellent adhesion to polyolefins, polyesters, and other polymers while providing outstanding low temperature performance.

Typical Physical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
Methyl Acrylate Content	Westlake	20 weight %
Melt Index (Condition 190°C/2.16 kg)	D 1238	8.0 g/10 min
Density	D 1505	941 kg/m ³ (0.941 g/cm ³)
Vicat Softening Temperature	D 1525	50°C (124°F)
Melting Point by DSC (T _m)	D 3418	84°C (183°F)
Brittleness Temperature	D 746	< -73°C (< -99°F)
Durometer Hardness Shore D Scale	D 2240	39
Tensile Stress @ Break (500 mm/min, 20 in/min)	D 638 Type IV	8.5 MPa (1,200 psi)
Elongation @ Break (500 mm/min, 20 in/min)	D 638 Type IV	600 %

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

The reported properties were measured from compression molded specimens prepared according to ASTM D 1928.

Processing

Processing conditions for methyl acrylate copolymer resins vary depending upon application, fabrication equipment, and resin use. These resins are thermally stable and process like LDPE.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.